

- 47 -


## [CLAIMS]

1. A heat-sensitive lithographic printing plate precursor comprising a support having a hydrophilic surface and a coating provided on the hydrophilic surface, said coating comprising in the order given a first layer containing an oleophilic resin soluble in an aqueous alkaline developer and a second layer capable of preventing the developer from penetrating into the first layer at unexposed areas, said second layer comprising a water-repellent compound selected from the group consisting of
- a polymer comprising siloxane and/or perfluoroalkyl monomeric units, and
  - a block- or graft-copolymer comprising a poly- or oligo(alkylene oxide) and a polymer or oligomer comprising siloxane and/ or perfluoroalkyl monomeric units, and
- wherein the alkali-solubility of said coating increases on heating and said coating comprises an infrared light absorbing dye characterised in that the infrared absorbing dye comprises at least one perfluoroalkyl group.
2. A lithographic printing plate precursor according to claim 1 wherein the perfluoroalkyl group is covalently linked to the infrared light absorbing dye.
3. A lithographic printing plate precursor according to claim 1 wherein the infrared light absorbing dye carries a charge and the perfluoroalkyl group is comprised in a counter ion and contains at least 6 fluorine atoms.
4. A lithographic printing plate precursor according to claim 1 wherein at least one perfluoroalkyl group is covalently linked to the infrared light absorbing dye and at least one perfluoroalkyl

- 48 -

group containing 6 or more fluorine atoms is comprised in a counter ion.

5. A lithographic printing plate precursor according to any of the preceding claims wherein the infrared light absorbing dye is selected from the group consisting of squarylium, croconate, merocyanine, cyanine, indolizine, pyrilium and metal dithioline dyes.
6. A lithographic printing plate precursor according to any of the preceding claims wherein the amount of the water-repellent compound in the coating is between 0.5 and 15 mg/m<sup>2</sup>.
7. A lithographic printing plate precursor according to any of the preceding claims wherein the second layer consists essentially of the water-repellent compound and the infrared light absorbing dye.
8. A lithographic printing plate precursor according to any of the preceding claims 1-4, 6 or 7 wherein the infrared light absorbing dye corresponds to the following formula:



- 49 -

wherein

$-L^1-$  and  $-L^2-$  independently represent a divalent linking;

$-E^1$  and  $-E^2$  independently represent a neutral, anionic or cationic terminal group selected from

5 alkyl,  $-OH$ ,  $-H$ ,  $-Cl$ ,  $-Br$ ,  $-F$  (neutral groups);

$-SO_3^-$ ,  $-SO_4^-$ ,  $-PO_3^{2-}$ ,  $-PO_4^{2-}$ ,  $-COO^-$  (anionic groups);

$-[NR^aR^bR^c]^+$  (cationic group);

$R^a$ ,  $R^b$  and  $R^c$  independently represent a hydrogen atom or an alkyl group;

10  $-A^1-$  and  $-A^2-$  independently represent  $-C_vF_{2v}-$ ,  $-[(CF_2)_2-O]_w-$ , a long chain alkyl group containing at least four carbon atoms, or an optionally substituted alkyl, alkenyl, aryl or aralkyl group;

with  $p_1$  and  $p_2$  are 0 or 1;

with  $v$  and  $w$  are 2 or an integer greater than 2;

15  $-Y^1-$  and  $-Y^2-$  independently represent  $-CR^9R^{10}-$ ,  $-S-$ ,  $-Se-$ ,  $-NR^{11}-$ ,  $-CH=CH-$  or  $-O-$ ;

$R^1$  to  $R^{11}$  each independently represent a hydrogen atom, an

optionally substituted alkyl, alkenyl, aryl or aralkyl group or a

20 group selected from a halogen atom,  $-NO_2$ ,  $-O-R^d$ ,  $-CO-R^d$ ,  $-CO-O-R^d$ ,  $-O-CO-R^d$ ,  $-CO-NR^dR^e$ ,  $-NR^dR^e$ ,  $-NR^d-CO-R^e$ ,  $-NR^d-CO-O-R^e$ ,  $-NR^d-CO-NR^eR^f$ ,  $-SR^d$ ,  $-SO-R^d$ ,  $-SO_2-R^d$ ,  $-SO_2-O-R^d$ ,  $-SO_2NR^dR^e$  or a perfluoroalkyl

group, each of said groups may optionally comprise a terminal group  $E$  defined above as  $-E^1$  and  $-E^2$  and/or wherein two adjacent groups selected from  $R^1$ ,  $R^2$ ,  $R^3$ ,  $R^4$ ,  $R^5$ ,  $R^6$ ,  $R^7$ ,  $R^8$ ,  $Y^1$  and  $Y^2$  together

25 form an optionally substituted 5- or 6- membered ring;

$R^d$ ,  $R^e$  and  $R^f$  independently represent a hydrogen or an optionally substituted alkyl, alkenyl, aryl or aralkyl group;

$Z^1$  and  $Z^3$  each independently represent a hydrogen atom, an alkyl group or  $Z^1$  and  $Z^3$  together represent the necessary atoms to

30 complete an optionally substituted 5- or 6- membered ring;

- 50 -

$Z^2$  represents a substituent selected from a hydrogen atom, an alkyl group, a halogen atom, an amino group, an arylthio group, an alkylthio group, an aryloxy group, an alkoxy group, a barbituric group or a thiobarbituric group, each of said groups being  
 5 optionally substituted;


X represents one or more optional counter ions having a total charge opposite to the dye and wherein X optionally comprises a perfluoroalkyl group containing at least 6 fluorine atoms;

with the proviso that at least one of the following substituents  
 10 contains a perfluoroalkyl group:




$-A^1-$ ,  $-A^2-$ ,  $R^1$  to  $R^{11}$  or X.

9. A printing plate precursor according to claim 8 wherein  $-Z^1$  and  $-Z^3$  together represent  $-(CH_2)_2-$  or  $-(CH_2)_3-$ .

10. A lithographic printing plate precursor according to claims 8  
 15 or 9 wherein the IR light absorbing dye corresponds to one of the following formulae:





- 51 -





wherein  $p_1$ ,  $p_2$ ,  $-L^1-$ ,  $-L^2-$ ,  $-A^1-$ ,  $-A^2-$ ,  $-E^1$ ,  $-E^2$ ,  $R^9$ ,  $R^{10}$ ,  $Z^2$  and X  
 5 have the same meaning as defined in claim 8.

11. A lithographic printing plate precursor according to claim 8  
 wherein the IR light absorbing dye corresponds to one of the  
 following formulae:







- 52 -



W



- 53 -



- 54 -

wherein

m is 2 or an integer greater than 2;

$R^{12}$  and  $R^{13}$  independently represent a hydrogen atom, an optionally substituted alkyl, alkenyl, aryl or aralkyl group or a  
5 perfluoroalkyl group which may optionally comprise a terminal group E defined as  $-E^1$  and  $-E^2$  in claim 8;

$R^{14}$  represents  $-(CH_2)_2-OCO-(CH_2)_2-(CF_2)_k-CF_3$ ;  
with k is 2 or an integer greater than 2;

W represents  $Cl^-$ ,  $Br^-$ ,  $I^-$ ,  $F^-$ ,  $ClO_4^-$ ,  $BF_4^-$ ;

10 G represents  $SO_3^-$ ,  $SO_4^-$  or  $COO^-$ .

15

20